

# Technical Data

## Tankguard CV



### Product description

Tankguard CV is a high-build epoxy coating with high conductivity. It is resistant to a wide range of chemicals and solvents.

---

### Recommended use

Interiors of tanks where antistatic coating is required.

---

### Film thickness and spreading rate

	Minimum	Maximum	Typical
Film thickness, dry (µm)	125	200	150
Film thickness, wet (µm)	250	400	300
Theoretical spreading rate (m <sup>2</sup> /l)	4	2,5	3,3

---

### Physical properties

Colour	Black
Solids (vol %)*	50 ± 2
Flash point	25°C ± 2 (Setaflash)
VOC	390 gms/ltr UK-PG6/23(97). Appendix 3
Gloss	Flat
Water resistance	Very good
Abrasion resistance	Very good
Solvent resistance	Excellent
Chemical resistance	Excellent

\*Measured according to ISO 3233:1998 (E)

---

### Surface preparation

All surfaces should be clean, dry and free from contamination. The surface should be assessed and treated in accordance with ISO 8504.

**Bare steel**

Cleanliness: Blast cleaning to min. Sa 2 ½ (ISO 8501 1:2007). Roughness: using abrasives suitable to achieve Grade Medium G (50 - 85 µm, Ry5) (ISO 8503-2).

**Other surfaces**

The coating may be used on other substrates. Please contact your local Jotun office for more information.

---

## Condition during application

The temperature of the substrate should be minimum 10°C and at least 3°C above the dew point of the air, temperature and relative humidity measured in the vicinity of the substrate. Good ventilation is usually required in confined areas to ensure proper drying. The coating should not be exposed to oil, chemicals or mechanical stress until fully cured.

---

## Application methods

<b>Spray</b>	Use airless spray
<b>Brush</b>	Recommended for stripe coating and small areas, care must be taken to achieve the specified dry film thickness.

---

## Application data

<b>Mixing ratio (volume)</b>	4:1
<b>Mixing</b>	4 parts Tankguard CV Comp. A (base) to be mixed thoroughly with 1 part Tankguard HB, Comp. B (curing agent).
<b>Induction time</b>	30 minutes.
<b>Pot life (23°C)</b>	8 hours (Reduced at higher temp.)
<b>Thinner/Cleaner</b>	Jotun Thinner No. 23
<b>Guiding data airless spray</b>	
<b>Pressure at nozzle</b>	15 MPa (150 kp/cm², 2100 psi)
<b>Nozzle tip</b>	0.46-0.69 mm (0.018-0.027")
<b>Spray angle</b>	40-80°C
<b>Filter</b>	Check to ensure that filters are clean.

---

## Drying time

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly. The figures given in the table are typical with:

- \* Good ventilation (Outdoor exposure or free circulation of air)
- \* Typical film thickness
- \* One coat on top of inert substrate

## Normal hardener

Substrate temperature	10°C	23°C	40°C
Surface dry	7 h	3,5 h	2 h
Through dry	24 h	6 h	4 h
Cured	14 d	7 d	3 d
Dry to recoat, minimum	24 h	12 h	6 h
Dry to recoat, maximum <sup>1</sup>	12 d	7 d	4 d

1. The surface should be free from chalking and contamination prior to application. If the maximum dry to recoat time is exceeded, please contact Jotun for advice.

The given data must be considered as guidelines only. The actual drying time/times before recoating may be shorter or longer, depending on film thickness, ventilation, humidity, underlying paint system, requirement for early handling and mechanical strength etc. A complete system can be described on a system sheet, where all parameters and special conditions could be included.

---

## Typical paint system

Tankguard CV                      2 x 150 µm                      (Dry Film Thickness)

Other systems may be specified, depending on area of use

---

## Storage

The product must be stored in accordance with national regulations. Storage conditions are to keep the containers in a dry, cool, well ventilated space and away from source of heat and ignition. Containers must be kept tightly closed.

---

## Handling

Handle with care. Stir well before use.

---

## Packing size

20 litre unit: 16 litres Tankguard CV, Comp. A (base) in a 20 litre container and 4 litres Tankguard HB, Comp. B (curing agent) in a 5 litre container.

---

## Health and safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

**For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Material Safety Data Sheet.**

---

## DISCLAIMER

The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product can be used under conditions beyond our control, we can only guarantee the quality of the product itself. We also reserve the right to change the given data without notice. Minor product variations may be implemented in order to comply with local requirements.

If there is any inconsistency in the text the English (UK) version will prevail.

Jotun is a World Wide company with factories, sales offices and stocks in more than 50 countries. For your nearest local Jotun address please contact the nearest regional office or visit our website at [www.jotun.com](http://www.jotun.com)

ISSUED 22 DECEMBER 2011 BY JOTUN  
THIS DATA SHEET SUPERSEDES THOSE PREVIOUSLY ISSUED

